

Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) **EP 1 512 583 A1**

(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:
09.03.2005 Bulletin 2005/10

(51) Int Cl.7: **B60R 13/10, G09F 13/04**

(21) Application number: **03102709.7**

(22) Date of filing: **05.09.2003**

(84) Designated Contracting States:
**AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
HU IE IT LI LU MC NL PT RO SE SI SK TR**
Designated Extension States:
AL LT LV MK

- **Prollius, Sven**
1831 Diegem (BE)
- **Reimann, Stefan**
1831 Diegem (BE)
- **Eberwein, Arnold**
1831 Diegem (BE)

(71) Applicant: **3M Innovative Properties Company**
St. Paul, Minnesota 55144-1000 (US)

(74) Representative: **Voortmans, Gilbert J.L. et al**
3M Europe S.A.,
Hermeslaan 7
1831 Diegem (BE)

(72) Inventors:
• **Frisch, Ruediger**
1831 Diegem (BE)

(54) **License plate for back illumination and method for making same**

(57) The present invention provides a license plate comprising a laminate that comprises:

- (i) a transparent polymeric support sheet (13);
- (ii) a transparent retroreflective sheet (11);
- (iii) one or more transparent adhesive layers (12) adhering said transparent polymeric support sheet (13) and said transparent retroreflective sheet (11) together; and
- (iv) indicia (14).

The license plate can be removably mounted to a light source for back lighting the license plate. The invention further describes a method of making the license plate and to a license plate assembly.

EP 1 512 583 A1

Description

[0001] The present invention relates to a license plate suitable for back illumination, i.e. a backlit license plate, that can be removably mounted to a light source such as for example an electroluminescent device. The present invention further provides a method for making a backlit license plate and to a license plate assembly.

[0002] Commonly employed license plates for motor vehicles for use on roads such as cars, busses and trucks, typically are illuminated from their front face when it is dark. In particular, the license plates typically have indicia representing the license plate number issued by the appropriate national authorities on a retroreflective background. This retroreflectivity enhances visibility of the plate during day time conditions and also during night time conditions when lights of other motor vehicles or street light impinges upon the front face of the license plate. But in order to meet regulatory requirements, the license plate also needs to be illuminated with lights arranged on the motor vehicles. Thus, typically, lights are arranged aside of the license plate so as to illuminate the front face of the license plate.

[0003] Such an arrangement has the disadvantage of limiting the design possibilities of a car manufacturer. In particular, the lights that need to be arranged along one or more sides of the license plate prevent the car manufacturer of making more appealing designs as the lights often appear as a disturbing element in the design. Furthermore, such front-lit license plates may suffer from a non-uniform illumination of the license plate.

[0004] To overcome this problem, DE 297 12 954 discloses a license plate arrangement that is illuminated from the back. In particular, this German utility model discloses a stiff transparent plastic plate on which the license plate number is depicted as opaque indicia. The stiff plastic plate is held in front of an electroluminescent foil through a holding frame. The electroluminescent foil when activated illuminates the plastic plate from the back. Such an arrangement has the disadvantage that no retroreflectivity is provided which is a requirement of the regulatory authorities of many countries. A further back-lit license plate is disclosed in US 5,692,327.

[0005] EP 1 262 373 describes a back-lit electroluminescent license plate arrangement that also provides retroreflectivity. In particular, this EP application discloses a housing in which there is arranged in the order given (from back to front) an electroluminescent foil, a transparent retroreflective sheet, a roughening layer such as a highly transparent film with a rough surface and a further transparent cover which closes the front opening of the housing such that all layers of the arrangement are held tightly together. It is taught that the roughening layer overcomes formation of Newton-rings which would otherwise form between the transparent front cover and the retroreflective sheet. The indicia of the license plate can be provided directly on the transparent cover or on a transparent film between the trans-

parent retroreflective sheet and the transparent cover. Although such license plate arrangement provides retroreflectivity and can be illuminated from the back, its manufacturing is complicated and expensive. Also, the manufacturing thereof is not compatible with methods by which the commonly used front lit license plates are made. Accordingly, the manufacturing of such plates requires investments in new manufacturing methods, which hampers the introduction of back lit license plate. Furthermore, when the license plate needs to be replaced, the whole arrangement would need to be replaced including the housing and the electroluminescent sheet. Such is highly undesirable from a cost perspective as well as from an environmental point of view. It might be contemplated though to make it possible for a user to open the housing and only replace the sheet with the indicia. However, such will likely cause the arrangement to be insufficiently sealed such that the quality of the license plate arrangement would deteriorate over time for example by moisture and dirt penetrating into the housing.

[0006] It would thus be desirable to find a further license plate that can be illuminated from the back and that also has retroreflectivity. Preferably, such license plate can be conveniently manufactured, at a low cost. Preferably the method of making the license plate will be compatible with the variety of existing license plate manufacturing methods. Desirably, the license plate can be easily replaced independent of the light source necessary to illuminate it. Preferably, the license plate also has a high durability and can meet regulatory requirements imposed by national authorities.

[0007] In one aspect, the present invention provides a license plate suitable for back illumination. The license plate comprises a laminate that comprises:

- (i) a transparent polymeric support sheet;
- (ii) a transparent retroreflective sheet;
- (iii) one or more transparent adhesive layers adhering said transparent polymeric support sheet and said transparent retroreflective sheet together; and
- (iv) indicia.

The license plate can be removably mounted to a light source for back lighting the license plate.

By the term 'transparent' as used in this application is generally meant that the respective sheet or layer allows light to pass there through without substantial portions thereof being absorbed. Accordingly, transparent materials in connection with the present invention can be optically clear and have a visible light transmission of 80 to almost 100%. The term transparent is however not meant to exclude translucent materials. Translucent materials may have a visible light transmission of only 30 to 80%.

By the term 'transparent retroreflective sheet' is meant that the sheet is capable of retroreflecting light that impinges on the surface of the sheet and is further trans-

parent in the sense set forth above. A transparent retroreflective sheet in accordance with the invention may be highly transparent (transmission for visible light of 80 to 99%) or may be translucent.

By the term 'front' as used in respect of the license plate is meant the side or face of the license plate that presents the license plate number in a right reading fashion to a viewer. By the term 'back' in respect of the license plate then is meant the side or face opposite the front, i.e. the side from which the license plate will be illuminated when in use.

[0008] The above-disclosed license plate offers the advantage of combining back lighting with retroreflectivity. Moreover, such plates can be easily produced in a generally cost effective way in existing equipment and manufacturing methods employed for making common license plates that are front lit. Still further, the obtained license plates can generally provide a high durability and can be used with a variety of light sources for back illumination. Moreover, the license plate can be easily replaced without having to replace part or all of the lighting arrangement.

[0009] In a further aspect, the present invention provides a license plate assembly comprising a light source and the license plate removably mounted in front of the light source.

[0010] In yet a further aspect of the invention, there is provided a method of making the license plate. The method comprises (i) adhering a transparent polymeric support and a transparent retroreflective sheet together with one or more transparent adhesive layers to obtain a laminate; (ii) applying indicia and (iii) dimensioning and shaping to obtain a license plate having a shape and dimension as desired. The steps of the method do not need to be applied in the order given and may be applied in any particular order.

License plate

[0011] The license plate comprises a transparent polymeric support sheet and a transparent retroreflective sheet adhered together by a transparent adhesive. The transparent polymeric support sheet will typically be a stiff polymeric support sheet. That is, although the transparent polymeric support sheet may be bended somewhat, it has a sufficient stiffness such that it cannot be folded or wrinkled as may be possible with a film or foil. Thus, the support sheet will typically have a thickness to provide such desired stiffness. Typically, the transparent support sheet will have a thickness between 0.2 and 5 mm, preferably between 0.3 and 3 mm and most preferably between 0.5 mm and 1.5 mm. The transparent polymeric support sheet may be comprised of a single polymer layer or may be comprised of several polymer layers of same or different composition.

[0012] A layer of the polymeric support sheet may be a thermoplastic polymer layer or may be a cross-linked polymer layer. Also, a combination of thermoplastic pol-

ymers layers and cross-linked polymer layers may be used.

[0013] Polymeric materials that may be used in the transparent polymeric support sheet include thermoplastic polymers such as polycarbonates, poly(meth)acrylates such as polymethyl methacrylate, polyolefins such as polyethylene and polypropylene, polyesters such as polyethyleneterephthalates and polyethylenenaphthalates, cellulose acetate, polyvinyl chloride and copolymers of acrylonitrile, styrene and butadiene. The transparent polymeric support may further include one or more layers of cross-linked material.

[0014] In a preferred embodiment, the transparent polymeric support sheet is cold-formable. By 'cold-formable' in connection with the invention is meant that raised indicia can be formed in the transparent polymeric support sheet at ambient temperature (20 to 35°C) for example through embossing or deep drawing and that such raised indicia are maintained at elevated temperatures to which the license plate may be exposed, e.g. when the motor vehicle is parked in the sun. This typically requires that the polymeric support has a sufficient heat stability, i.e. the polymeric support sheet should typically be heat stable upto temperatures of 60°C to 85°C. Without sufficient heat stability, the number of the license plate may fade over time or become distorted. This will be particularly the case when the indicia are cold-formed through embossing because of stress forces created in the polymeric support sheet during the embossing. Examples of transparent polymeric support sheets that are cold-formable include polymeric support sheets comprising polycarbonate. Also, a polymeric support sheet that is cold-formable may be obtained from a multi-layer construction including one or more thermoplastic polymers enumerated above and one or more layers of a cross-linkable material. Upon cold-forming the indicia in the polymeric support sheet, the cross-linkable material may be cross-linked to a polymeric cross-linked material. Thus, the one or more layers of polymeric cross-linked material will provide the desired heat stability because the cross-linked material will prevent the thermoplastic layers of the multi-layer sheet from flowing, which would cause the cold-formed indicia to disappear. Still further, a cold-formable polymeric support sheet may comprise one or more layers that comprise a cross-linkable thermoplastic polymer composition. In the non cross-linked state, the polymeric support sheet can be readily cold-formed to provide indicia therein. Subsequent to forming the indicia, the cross-linkable thermoplastic polymer composition can be cross-linked such that the layer(s) loses its thermoplastic properties and sufficient heat stability may thereby be provided.

[0015] The cross-linkable material that can be used includes materials that may be heat cross-linked, cross-linked by light including visible light and UV light, cross-linked by electron beams or by gamma irradiation. The cross-linkable material may be a composition that is

based on cross-linkable monomeric or low molecular weight components, cross-linkable polymer components as well as combinations thereof. Suitable cross-linkable materials that can be used include for example an electron beam curable vinyl chloride-acrylate copolymer as disclosed in US 4,889,895, a radiation curable polyvinyl chloride as disclosed in US 4,631,229, an epoxy based curable composition as described below for use in the adhesive layer.

[0016] The transparent retroreflective sheet for use in connection with the present invention can be a single layer sheet but is generally a multi-layer sheet. The retroreflective sheet may be a microsphere based retroreflective sheet or a so-called cube corner based retroreflective sheet. Microsphere-based sheeting, sometimes referred to as "beaded sheeting," is well known in the art and includes a multitude of microspheres, e.g. glass or ceramic microspheres, typically at least partially embedded in a binder layer, and associated specular or diffuse reflecting materials. The reflective material should be provided functionally behind the microspheres. By 'functionally behind' is meant that the reflective layer is provided behind the microspheres in such a way that in conjunction with the microspheres light will be retroreflected. Typically, this means that the reflective layer is directly provided on the microspheres or is slightly spaced away, through a space coat, from the microspheres to adjust to the focal point of the microspheres. Illustrative examples of microsphere-based sheeting are disclosed in U.S. Pat. Nos. 4,025,159 (McGrath); 4,983,436 (Bailey); 5,064,272 (Bailey); 5,066,098 (Kult); 5,069,964 (Tolliver); and 5,262,225 (Wilson). The reflective material in one embodiment of this invention can be a reflective metal layer. When the reflective layer is a reflective metal layer, it should be provided at such a thickness that enough reflection can occur and at the same time sufficient transparency is obtained as well. Preferably, a dielectric mirror is provided as the reflective layer since a dielectric mirror is typically transparent.

[0017] The dielectric mirrors may be similar to known dielectric mirrors disclosed in U.S. Pat. Nos. 3,700,305 and 4,763,985. In using dielectric mirrors with microspheres, the microspheres typically have a refractive index n_2 and have a layer of transparent material disposed thereon which has a refractive index n_1 . The opposite face of the transparent material having refractive index n_1 , is in contact with a material having a refractive index n_3 . Both n_2 and n_3 have a refractive index of at least 0.1, preferably at least 0.3, higher or lower than n_1 . The transparent material is a layer typically having an optical thickness corresponding to odd numbered multiples (that is, 1, 3, 5, 7 ...) of about one-quarter wavelength of light in the wavelength range of about 380 to about 1,000 nanometers. Thus, either $n_2 > n_1 < n_3$ or $n_2 < n_1 > n_3$, and the materials on either side of the transparent layer may be either both higher or both lower in refractive index than n_1 . When n_1 is higher than both n_2 and

n_3 , n_1 is preferably in the 1.7 to 4.9 range, and n_2 and n_3 are preferably in the 1.2 to 1.7 range. Conversely, when n_1 is lower than both n_2 and n_3 , n_1 is preferably in the 1.2 to 1.7 range, and n_2 and n_3 are preferably in the 1.7 to 4.9 range. The dielectric mirror preferably comprises a contiguous array of materials, at least one being in layer form, having an alternating sequence of refractive indices. In a preferred embodiment the contiguous array has from two to seven layers, preferably three to five layers. Desirably all are light transparent materials and are clear or essentially colorless to minimize light absorption and maximize light transmission of the retroreflective sheet.

[0018] Among the many compounds that may be used in providing transparent materials within the desired refractive index range are: high index materials such as CdS, CeO_2 , CsI, GaAs, Ge, InAs, InP, InSb, ZrO_2 , Bi_2O_3 , ZnSe, ZnS, WO_3 , PbS, PbSe, PbTe, RbI, Si, Ta_2O_5 , Te, TiO_2 ; low index materials such as Al_2O_3 , AlF_3 , CaF_2 , CeF_3 , LiF, MgF_2 , NaCl, Na_3AlF_6 , ThOF_2 , elastomeric copolymers of perfluoropropylene and vinylidene fluoride et cetera. Other materials are reported in Thin Film Phenomena, K. L. Chopra, page 750, McGraw-Hill Book Company, New York, (1969). Preferred succeeding layers contain cryolite (Na_3AlF_6) and zinc sulfide.

Dielectric mirrors or similar multi-layer reflective coatings can also be used in combination with cube corner sheeting as disclosed in e.g. JP 06-347622, US 6,172,810, US 6,224,219, US 6,243,201 and US 6,350,034.

[0019] Cube corner sheeting, sometimes referred to as prismatic, microprismatic, triple mirror or total internal reflection sheetings, typically include a multitude of cube corner elements to retroreflect incident light. Cube corner retroreflectors typically include a sheet having a generally planar front surface and an array of cube corner elements protruding from the back surface. Cube corner reflecting elements include generally trihedral structures that have three approximately mutually perpendicular lateral faces meeting in a single corner, i.e. a cube corner. In use, the retroreflector is typically arranged with the front surface disposed generally toward the anticipated location of intended observers and the light source. Light incident on the front surface enters the sheet and passes through the body of the sheet to be reflected by each of the three faces of the elements, so as to exit the front surface in a direction substantially toward the light source. In the case of total internal reflection, the air interface must remain free of dirt, water and adhesive and therefore is enclosed by a sealing film. Alternatively, reflective coatings may be applied on the lateral faces of the cube corners. Suitable reflective coatings that can be applied include transparent reflective metal layers or a dielectric mirror as described. When the cube corner elements are provided with a reflective coating they can also be used in a configuration where they are generally positioned to the anticipated

location of an intended observer.

[0020] Polymers for cube corner sheeting include poly (carbonate), poly(methyl methacrylate), poly(ethylene terephthalate), aliphatic polyurethanes, as well as ethylene copolymers and ionomers thereof. Cube corner sheeting may be prepared by casting directly onto a film, such as described in U.S. Patent No. 5,691,846 (Benson, Jr.). Polymers for radiation-cured cube corners include cross-linked acrylates such as multifunctional acrylates or epoxies and acrylated urethanes blended with mono- and multifunctional monomers. Further, cube corners may be cast on to plasticized polyvinyl chloride film for more flexible cast cube corner sheeting. These polymers are often employed for one or more reasons including thermal stability, environmental stability, clarity, excellent release from the tooling or mold, and capability of receiving a reflective coating.

[0021] In an embodiment of this invention the cube corner sheeting may have a further polymeric layer bonded to the side of the cube corner sheeting that has the cube corner elements so as to form a plurality of closed cells in which an air interface is provided to the cube corner elements. Illustrative examples of cube corner-based retroreflective sheeting are disclosed in U.S. Pat. Nos. 4,588,258 (Hoopman); 4,775,219 (Appledorn et al.); 4,895,428 (Nelson); 5,138,488 (Szczech); 5,387,458 (Pavelka); 5,450,235 (Smith); 5,605,761 (Burns); 5,614,286 (Bacon Jr.) and 5,691,846 (Benson, Jr.).

[0022] The transparent polymeric support sheet and the retroreflective sheet are bonded together with one or more adhesive layers. The term 'bonded together' includes not only a configuration where the support sheet and retroreflective sheet are directly bonded to each other by the adhesive layer but also includes the option where one or more intermediate layers are present. For example, the retroreflective sheet and/or the polymeric support sheet may be coated with one or more primer layers to assure firm adhesion of the adhesive layer to these respective sheets. Still further, the sheets may be bonded to each other with two or more adhesive layers that are provided on opposite major sides of a transparent carrier layer.

[0023] The one or more adhesive layers suitable for bonding the support sheet and retroreflective sheet together should be transparent. Preferably the adhesive layer(s) will be at least 80%, preferably at least 90% transmissive for visible light. The adhesive layers preferably show good weatherability properties, have good thermal stability and are moisture resistant. The adhesive layer should furthermore create a high bond strength to each of the sheets such that the license plate cannot be delaminated. A sufficient bond strength typically means that the peel force necessary to delaminate the sheets from each other is at least 2 N/cm, preferably at least 4 N/cm. The adhesive layer may comprise a pressure sensitive adhesive, a heat-activatable adhesive, i.e. an adhesive that requires heat activation to de-

velop a bond or a cross-linkable adhesive. Examples of adhesives include pressure sensitive adhesives (PSA) based on acrylic polymers, based on silicones or based on polyolefins as disclosed in Handbook of Pressure Sensitive Adhesive Technology (third edition) D.Satas, Ed. Satas and Associates, Warwick RI/USA, 1989 on pages 444-514, 550-556 and 423-442 respectively. Adhesives that may be used to bond to substrates having a low surface energy such as polyolefin or polycarbonate, include for example pressure sensitive adhesives based on an acrylic copolymer of one or more alkyl esters of acrylic or methacrylic acid and a vinyl ester as disclosed in for example EP 1 318 181 or a pressure sensitive adhesive as disclosed in EP 1 245 656 which discloses a pressure sensitive adhesive composition that contains (i) the reaction product obtainable from a precursor composition comprising one or more alkyl esters of acrylic or methacrylic acid, one or more copolymerizable monomers that have a Lewis base functionality and optionally one or more cross-linkers and (ii) one or more tackifying resins. Still further pressure sensitive adhesives that can be used to create a strong bond in particular to a polycarbonate substrate include those disclosed in US 4,181,752, US 4,418,120 and WO 95/13331. These references teach PSA that are based on acrylic polymers that are cross-linked without however losing their pressure sensitive adhesive properties. Further adhesive layer compositions that may be used include those that are based on a curable composition that upon curing creates a strong adhesive bond between the sheets. Suitable curable compositions that may be used include radiation curable epoxy compositions. Such compositions may be applied in their uncured (or partially cured) state between the sheets. Upon curing of the laminate through radiation, e.g. UV radiation or electron beam radiation, a firm and durable bond can be created. Examples of epoxy based curable compositions can be found in e.g. EP 1026218 and EP 620 259 disclosing a UV or electron beam curable epoxy composition comprising an epoxy resin, a polyester and optionally a photoinitiator. Still further epoxy-based adhesive compositions are disclosed in US 4,622,349, US 4,812,488, US 4,920,182, US 4,256,828 and EP 276716. Further, according to a particular embodiment of the invention, an epoxy based pressure sensitive thermosetting adhesive can be used as disclosed in US 5,086,088. This US patent discloses a pressure-sensitive thermosetting adhesive comprising from about 30% to about 80% by weight of a photopolymerizable prepolymeric or monomeric syrup containing an acrylic ester and a polar copolymerizable monomer, from about 20% to about 60% by weight of an epoxy resin or a mixture of epoxy resins containing no photopolymerizable groups, from about 0.5% to about 10% by weight of a heat-activatable hardener for the epoxy resin, from about 0.01% to about 5% of a photoinitiator, and from 0% to about 5% of a photocrosslinking agent.

[0024] The license plate typically will have shape and

dimensions conforming to relevant regulatory requirements. Also, the license plate will comprise indicia that represent the number of the license plate as may be issued by a relevant authority. In addition to indicia representing the number of the license plate, the license plate may comprise further indicia such as for example indicia showing the country letter or indicia giving indications of the manufacturer of the license plate and/or date of issuance of the license plate. Some of these latter indicia may be in machine readable form such as for example in the form of a bar code. The indicia of the license plate can be formed by any technique used in producing license plates. For example, the indicia, in particular those representing the number of the license plate, may be printed e.g. by thermal transfer printing or by ink jet printing or the indicia may be cut out of a colored adhesive film and glued on the plate. The indicia may be printed on or glued on the front face of the license plate or they can be buried in the license plate. In addition to printed indicia, the present invention also allows for the indicia to be raised. By raised indicia is meant that the indicia project from the front face of the license plate. Typically the indicia can be raised by 0.3 to 20 mm relative to the background of the license plate, preferably 0.5 to 15mm. Raised indicia may be obtained by deep drawing but are preferably made by embossing a laminate of the transparent polymeric support sheet and the retroreflective sheet. Preferably the raised surface of the indicia will be colored to render the indicia opaque or at least less transparent than the background of the license plate. Typically the raised surface may be colored by hot foil stamping or by roll coating with inks.

Method of making the license plate

[0025] The license plate can be made by equipment and techniques that are typically used to produce conventional front lit license plates. Thus, according to one embodiment of the method, the license plate may be obtained by adhering the transparent polymeric support sheet and retroreflective sheet together followed by dimensioning and shaping the obtained laminate as desired. Alternatively however, the respective sheets forming the laminate may be dimensioned and shaped before being adhered together. Also, the license plate may be shaped and dimensioned so as to adapt it for being removably mounted to a light source. For example, a rim may be provided along one or more sides of the license plate. Such a rim may then be used to clamp the license plate against the light source. Alternatively, such a rim may locate with one or more corresponding channels on the light source such the license plate may slide into these channels. Still further, portions of the license plate may be projecting beyond the required dimension of the license plate along one or more sides of the license plate and these may then be used to clamp the plate to the light source.

[0026] The laminate may then be embossed to pro-

vide raised indicia. Such embossing is preferably carried out at ambient temperature by pressing a metallic or thermoset polymeric template having a representation of the indicia on the license plate. Following this operation, the raised surfaces of the indicia may be colored by hot stamping a colored wax ribbon thereon. Accordingly, this method allows for making back-lit license plate using the equipment that is typically used to make embossed metallic license plates. Alternatively, the raised indicia may be thermoformed by subjecting the laminate to heat while pressing a template representing the indicia on the laminate.

[0027] Back-lit license plates where the indicia are printed by e.g. a thermal transfer printer or inkjet printer can equally be produced with existing manufacturing equipment. For example, such printed license plates are used in the UK. Thus, to produce back-lit license plates that have printed indicia, a laminate of the polymeric support sheet and the retroreflective sheet may be printed on the front face with the indicia. Alternatively, the indicia may be first printed on the retroreflective sheet before it is laminated with the support sheet. Still further, the support sheet, if it defines the front face of the license plate, may be reverse printed before being laminated with the retroreflective sheet. Yet further, an additional transparent film may be included in the laminate which may be provided with the printed indicia. Thus, the same laminate can be used for a variety of existing license plate manufacturing methods.

License plate assembly

[0028] The license plate can be removably mounted to a variety of light sources that may be used to provide back lighting. By "removably mounted" is meant that the license plate can be mounted on the light source, removed therefrom and preferably mounted again to the light source. Generally, the mounting of the license plate to the light source is simple and easy and can be practiced by a user or owner of a car. For example, the license plate may be mounted to the light source using screws in much the same way as mounting of conventional license plates. Alternatively, the license plate may be clamped on the light source by means provided on the light source or the license plate may be mounted to the light source through the aid of a frame.

[0029] As mentioned above, the license plate can be used with a variety of light sources that have been used or disclosed for back lighting license plates. For example, the light source may comprise an electrically activatable layer or film that upon electrical activation emits light. Examples thereof include electroluminescent films such as for example those disclosed in WO 98/20375, which describes retroreflective signs such as billboards that are illuminated with an electroluminescent film. Generally, an electroluminescent layer or film will comprise a polymeric binder in which an electroluminescent material is dispersed. Such electroluminescent material

may be selected according to a desired color to be emitted and a mixture of different electroluminescent material can be used. The electroluminescent material is typically an inorganic substance. However, organic electroluminescent materials are known as well and can be used also. Organic electroluminescent materials are known in the art as Organic Light Emitting Diodes (OLED). OLED's typically comprise on a substrate, one or more organic layers between two electrodes. The organic layers can be electrically activated with the electrodes as a result of which they start emitting light. The physical principle on which light is produced by the organic layers is known as "Injection electroluminescence". Thus, an organic light emitting diode (OLED) typically comprises an organic light emitting layer disposed between two electrodes, whereby the organic light emitting layer luminesces when electricity flows between the electrodes. OLED are described in for example US 6,608,333 and US 6,501,218.

[0030] The light source for use in the license plate assembly may also comprise conventional Light Emitting Diodes (LED). Furthermore, according to a particular embodiment, the light source may comprise a light guide having a front face to which the license plate can be removably mounted, a back face opposite thereto and one or more side faces and (ii) a light source for illuminating the light guide arranged along at least portion of at least one of the side faces, the other side faces generally being closed so as to not to allow light to escape there through. The light source that is used in the edge lighting of the light guide is typically an elongate light source. An elongate light source emits light substantially along its longitudinal direction and comprises an elongated luminant, like a light tube, e.g. a fluorescent tube, or several individual luminants spaced from each other and arranged adjacent to each other along the longitudinal direction of the light source. Accordingly, an elongate light source can comprise a linear array of separate light emitting elements.

[0031] Within the light guide, light is transmitted by total internal reflection at the front and back and side faces until the light rays impinge onto the front face and onto the light-transmissive retro-reflective film at an angle at which the light is transmitted out of the front face of the light guide. The light guide may be a hollow or a solid light guide.

[0032] The amount of light extracted out of the front face of a light guide can be enhanced by light-scattering particles added to the transparent material of the light guide. Moreover, a back reflector can be arranged at the back face of the light guide. Reflectors can also be arranged at the side faces of the light guide. Both the back reflector and the side face reflectors preferably are diffuse reflective, specular reflective, or scattering reflective films with high reflection efficiency. Arranging reflectors and, in particular, highly diffuser or specular or scattering reflective films along the back and side faces of the light guide provides for a light guide in which light

can escape exclusively through the front face so that most of the light of the light source can be used for illuminating the license plate. Accordingly, such a design is highly efficient with regard to the required brightness, even illumination, and power consumption.

[0033] Moreover, other light extraction mechanisms, films or paints (in addition to, or as an alternative to, the reflectors mentioned before) can be used with the light guide. Also light-extraction elements printed onto a surface of the light guide (e.g. dots of variable size, shape and density) can be employed. Such arrangements are described, for example, in US-A-5,736,686; 5,649,754; 5,600,462; 5,377,084; 5,363,294; 5,289,351; 5,262,928; 5,667,289; and 3,241,256. Other light extraction arrangements that can be practiced are described in US-A-5,618,096, WO-A-92/05535, and WO-A-01/71248.

[0034] The light source of the license plate may be provided as a device that can be removably mounted to the body of the motor vehicle or may be provided as an integral part of the motor vehicle body.

[0035] The invention is described in more detail below with reference to the following drawings illustrating particular embodiments of the invention without however intending to limit the invention thereto. Also the drawings are purely schematic drawings in which the various dimensions of the features shown may have been exaggerated and the relative proportion of the dimensions of the various features shown in the drawings will generally not correspond to their proportion in the actual embodiment illustrated by the schematic drawing.

[0036] Figure 1 represents a view at the front face of a license plate suitable for illumination from the back. Figures 2 to 8 show a cross-section along line A in figure 1 illustrating various embodiments of the license plate.

Figure 9 shows a license plate assembly of the license plate removably mounted before a light source.

[0037] Figure 1 shows a license plate 200 comprising indicia 210 that define the number of the license plate as issued by an authority. License plate 200 further shows barcode 220 which may present additional information regarding the license plate such as source of its manufacturing.

[0038] Figure 2 illustrates a first embodiment of the license plate. This embodiment as well as any of the following embodiments illustrated by figures 3 to 8 are illustrated by showing a cross-section of the license plate along line A in figure 1. Same features of the license plates shown in figures 2 to 8 will be represented by the same numerals. As shown in figure 2, license plate 10 comprises a transparent retroreflective sheet 11 adhered by means of transparent adhesive layer 12 to transparent polymeric support sheet 13. In use, the retroreflective sheet 11 will be arranged to face the light source and transparent polymeric support sheet 13 will face an observer. License plate 10 contains raised indicia 14 that on their raised surface have been colored, e.g. a black color to render them opaque or less transpar-

ent relative to the background of the license plate. Raised indicia 14 have been formed by embossing a laminate of the transparent polymeric support sheet 13 and retroreflective sheet 11. As a result thereof, the back side of license plate 10 contains a recess 16 corresponding to the shape of indicia 14 located opposite thereto at the front face of license plate 10. In the embodiment shown in figure 2, retroreflective sheet 11 comprises a cube corner based sheeting having a polymeric layer 11c having on one major side cube corner elements 11d. Cube corner elements 11d are protected by a seal film 11a that is sealed to the polymeric layer 11c by seals 11b, e.g. created by thermosealing, thus creating closed cells 11e that provide an air interface to the cube corner elements 11d. When license plate 10 is arranged on a light source with retroreflective sheet 11 facing the light source, light will penetrate through retroreflective sheet 11, adhesive layer 12 and transparent polymeric support sheet 13 such that the light of the light source will be seen by an observer at background areas of the license plate. In the areas where indicia 14 are provided, the light of the light source will be blocked at least partially by printing 15 and thus no or less light will be seen by the observer at these places. Thus, license plate 10 will show dark indicia on a illuminated background.

[0039] License plate 20 illustrated in figure 3 uses the same retroreflective sheet 11 as used in license plate 10 illustrated in figure 2. However, the layer arrangement in license plate 20 is reversed such that transparent polymeric support sheet 13 now defines the back side of the license plate, i.e. the side that in use will face the light source, and retroreflective sheet 11 now defines the front face of the license plate.

[0040] The high transparency of the retroreflective sheets used in the embodiments shown in figure 2 and 3 offers the advantage that the required levels of illumination can be readily adjusted through the transparency of the other layers. Furthermore levels of retroreflection as may be required by regulations can be easily achieved by adjusting the transparency of the adhesive layer or transparent polymeric support sheet or optional further layers in the embodiment illustrated in figure 2.

[0041] License plate 30 illustrated in figure 4 uses a beaded retroreflective sheeting 32. beaded retroreflective sheeting 32 comprises glass or ceramic microspheres 32b that are partially embedded in a binder layer 32e and that are protected by topcoat 32a. Functionally behind the microspheres 32b is a reflective layer 32c. Reflective layer 32c may be a translucent reflective metal layer but is preferably a dielectric mirror as described above. Between the microspheres and the reflective layer 32c there may be provided a space coat as described above. Also, depending on the nature and composition of the adhesive layer, the binder layer 32e may not be required and the microspheres may then be embedded in adhesive layer 12. Retroreflective sheet 32 is arranged such that the microspheres will be facing

towards an observer and the reflective layer is behind the microspheres from the viewpoint of the observer. While license plate 30 has the retroreflective sheet 32 at its front face, license plate 40 (figure 5) shows the opposite arrangement where the retroreflective sheet 32 is at the back side of the license plate.

[0042] Figure 6 illustrates license plate 50 that uses retroreflective sheet 51. Retroreflective sheet 51 is a cube corner based sheeting having a polymeric layer having cube corner elements 51c on one major side. These cube corner elements are provided with a transparent or translucent reflective layer 51a and the cube corner elements are in-between filled with transparent adhesive layer 12. Reflective layer 51a may be a translucent metal layer but is preferably a dielectric mirror. In the embodiment shown in figure 6, the cube corners are facing towards an observer viewing license plate 50 from the front. Such an arrangement is known as a reverse-cube arrangement.

[0043] In figure 7, license plate 60 uses retroreflective sheet 61. Retroreflective sheet 61 is a cube corner based sheeting having polymeric layer having cube corner elements 61c on one major side. These cube corner elements are provided with a transparent or translucent reflective layer 61a and the cube corner elements are in-between filled with transparent adhesive layer 12. Reflective layer 61a may be a translucent metal layer but is preferably a dielectric mirror. In the embodiment shown in figure 7, the cube corners are facing away from an observer viewing license plate 60 from the front as is typically the case when using cube corner retroreflective sheeting.

[0044] Figure 8 illustrates an embodiment of a license plate according to the invention wherein the indicia are provided by printing. As shown, license plate 70 has a transparent retroreflective sheet 11 on the back side and a transparent polymeric support sheet on the front face glued together by transparent adhesive layer 12. Indicia 71 are provided on top of the polymer support sheet 13 but could also be buried in the license plate by reverse printing the polymer support sheet before it is adhered to retroreflective sheet 11.

[0045] Figure 9 illustrates a license plate assembly according to the invention. License plate assembly 100 comprises a light source that consists of a light guide 102 and an elongated light source 101 lighting the light guide from one of its side faces. On the front face of the light guide is arranged license plate 20. License plate 20 is removably mounted to the light source by clamping it in frame 103 of the license plate assembly 100.

Claims

1. License plate suitable for back illumination, said license plate comprising a laminate comprising:

(i) a transparent polymeric support sheet;

- (ii) a transparent retroreflective sheet;
 (iii) one or more transparent adhesive layers adhering said transparent polymeric support sheet and said transparent retroreflective sheet together; and
 (iv) indicia and
- wherein said license plate can be removably mounted to a light source for back lighting the license plate.
2. License plate according to claim 1 wherein said indicia comprise raised structures.
 3. License plate according to claim 1 wherein said indicia comprise raised structures having a thickness of 0.3 mm to 20 mm.
 4. License plate according to any of the previous claims wherein said indicia are opaque or have a reduced transparency relative to background areas of the license plate.
 5. License plate according to any of the previous claims comprising indicia obtainable by embossing said laminate.
 6. License plate according to any of the previous claims wherein said polymeric support sheet is selected from the group consisting of polycarbonate and a multi-layer laminate comprising two or more transparent thermoplastic polymeric layers bonded together by one or more layers of a transparent cross-linked material.
 7. License plate according to any of the previous claims wherein said transparent retroreflective sheet comprises a retroreflective sheet comprising a layer of glass and/or ceramic microspheres and a reflective layer, said reflective layer being provided on said layer of glass and/or ceramic microspheres.
 8. License plate according to claim 7 wherein said reflective layer comprises one or more translucent reflective metal layers and/or one or more dielectric mirror layers.
 9. License plate according to any of claims 1 to 6 wherein said transparent retroreflective sheet comprises a cube corner layer having opposite first and second surfaces, said first surface being generally planar and said second surface having a plurality of cube corner elements protruding therefrom.
 10. License plate according to claim 9 wherein said cube corner elements are provided with a reflective layer.
 11. License plate according to claim 9 wherein a further polymeric layer is bonded to said second surface of said cube corner layer so as to form a plurality of closed cells in which an air interface is provided to said cube corner elements.
 12. License plate assembly comprising a light source and a license plate as defined in any of claims 1 to 11 removably mounted in front of said light source.
 13. License plate assembly according to claim 12 wherein said light source comprises an electroluminescent device or a lighting device comprising (i) a light guide having a front face to which said license plate can be removably mounted, a back face opposite thereto and one or more side faces and (ii) a light source for illuminating said light guide arranged along at least portion of at least one of said side faces.
 14. License plate assembly according to claim 12 wherein said light source is an integral part of a motor vehicle body.
 15. Method for making a license plate as defined in any of claims 1 to 11 comprising:
 - (i) adhering a transparent polymeric support and a transparent retroreflective sheet together with one or more transparent adhesive layers to obtain a laminate;
 - (ii) applying indicia; and
 - (iii) dimensioning and shaping to obtain a license plate having a shape and dimension as desired.
 16. Method according to claim 15 wherein applying said indicia comprises embossing said indicia in said laminate.
 17. Method according to claim 16 wherein applying said indicia further comprises printing colour on said indicia formed by said embossing.




Fig. 1

Fig. 1




Fig. 2




Fig. 3




Fig. 4




Fig. 5




Fig. 6




Fig. 7




Fig. 8




Fig. 9



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number

EP 03 10 2709

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
Y	US 5 692 327 A (SKINNER DOYLE P ET AL) 2 December 1997 (1997-12-02) * column 3, line 16 - line 31 * * column 5, line 13 - line 27 * * figures 2,3 *	1,4,12, 15	B60R13/10 G09F13/04
Y,D	EP 1 262 373 A (FER FAHRZEUGELEK K GMBH) 4 December 2002 (2002-12-04) * column 3, line 27 - line 39 *	1,4,12, 15	
A	US 2003/090797 A1 (MUELLER MICHAEL) 15 May 2003 (2003-05-15) * paragraph [0027] - paragraph [0029]; figure 1 *	1	
A	EP 0 360 420 A (MINNESOTA MINING & MFG) 28 March 1990 (1990-03-28) * page 5, line 15 - page 7, line 3; figure 4 *	7,8	
A	DE 102 47 708 A (FITZKE WERBETECHNIK ;VOLKSWAGENWERK AG (DE)) 14 August 2003 (2003-08-14) * paragraph [0008] - paragraph [0011]; figure 2 *	1-3,12, 15	TECHNICAL FIELDS SEARCHED (Int.Cl.7) B60R G09F
The present search report has been drawn up for all claims			
Place of search MUNICH		Date of completion of the search 18 December 2003	Examiner Douhet, H
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

4

EPO FORM 1503 (3.12.02) (P04C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 03 10 2709

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

18-12-2003

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 5692327	A	02-12-1997	NONE	
EP 1262373	A	04-12-2002	DE 20109237 U1	09-08-2001
			DE 20201224 U1	18-04-2002
			EP 1262373 A2	04-12-2002
			JP 2003108044 A	11-04-2003
			US 2002178627 A1	05-12-2002
US 2003090797	A1	15-05-2003	DE 10044882 A1	21-03-2002
			CN 1436343 T	13-08-2003
			DE 20022563 U1	15-11-2001
			WO 0223509 A2	21-03-2002
			EP 1317747 A2	11-06-2003
EP 0360420	A	28-03-1990	US 5008142 A	16-04-1991
			AT 136124 T	15-04-1996
			AU 619878 B2	06-02-1992
			AU 3923489 A	08-03-1990
			CA 1336300 C	11-07-1995
			DE 68926081 D1	02-05-1996
			DE 68926081 T2	28-11-1996
			EP 0360420 A2	28-03-1990
			IE 73485 B1	04-06-1997
			JP 3250615 B2	28-01-2002
			JP 11288231 A	19-10-1999
			JP 2113078 A	25-04-1990
			JP 3038218 B2	08-05-2000
			KR 145078 B1	15-07-1998
			US 5256721 A	26-10-1993
			US 5262225 A	16-11-1993
			ZA 8905913 A	30-05-1990
DE 10247708	A	14-08-2003	DE 20201377 U1	18-04-2002
			DE 10247708 A1	14-08-2003
			WO 03064210 A1	07-08-2003

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82